



**Sikafloor 359 N**

Release 1\* - 23.10.2006

**\* Chemical Resistance \***

No.	Test Media & Test Temperature	Duration Of Impact: Method:	1 day		3 days		7 days	42 days
			Immersion Test	Spillage Test	Immersion Test	Spillage Test	Immersion Test	Immersion Test
001	DIBT-Test Media 01	RT	A/D	A	C	A/D	C	C
002	DIBT-Test Media 02.1	RT	A/D	A	A/D	A	A/D	A/D
003	DIBT-Test Media 03	RT	A/D	A	A/D	A	A/D	A/D
004	DIBT-Test Media 04b	RT	A/D	A/D	A/D	A/D	A/D	A/D
005	DIBT-Test Media 05a	RT	A/D	A	C	A	C	C
006	DIBT-Test Media 05b	RT	B	A/D	B/D	A/D	B/D	B/D
007	DIBT-Test Media 07b	RT	A/D	A/D	A/D	A	A/D	A/D
008	DIBT-Test Media 10	RT	A/D	A/D	A/D	B/D	A/D	A/D
009	DIBT-Test Media 11	RT	A	A	A	A	A	A
010	DIBT-Test Media 12	RT	A	A	A	A	A	A
011	DIBT-Test Media 14.1	RT	A	A	A/D	A/D	A/D	A
012	DIBT-Test Media 14.2	RT	A/D	A	A/D	A/D	A/D	A/D

\* re-conditioning

**Resistance Classes**

- A resistant - slight loss of hardness (0-20% Shore D), no blisters, no delamination, no or slight swelling
- B limited resistance - moderate loss of hardness (20-40% Shore D), no blisters, no delamination, noticeable swelling
- C unstable - strong loss of hardness (>40% Shore D) or blisters or delamination or partial / total destruction of layer
- D discoloration or loss of gloss / bleaching